

Codice: 6BA000

Topkapi Opaca

ONE COMPONENT CLEAR MATT VARNISH



One-component clear matt varnish for wood. Recommended for a matt finish on interiors of wooden boats, for furniture frames and all wood substrates. Easy to brush, provides good characteristics of adhesion and resistance in marine environment.

Techical Characteristics		Application Data	
Paint Type	One component	Application	Brush-Roller-Spray
Binder type A	Alkyd-synthetic	Brush-Roller	15-20% Diluent 107 or 109
Specific gravity kg/lt (±0,05)	0,950	Spray	20-30% Diluent 900
Solids content (volume) ±2	47%	Touch dry	6 h (20°C)
Viscosity Ford ø 8 at 20°C ±2	20-25	Recoat time	24 h (20°C)
Shelf life (+10+30°C)	18 months in airtight cans	Application temperature	Between +10 C et +40 C
		Relevant humidity	Less than 80%
		Dry film thickness advised	40 microns by hand
		Theoret. coverage m2/Lt	10

SURFACE PREPARATION AND APPLICATION

Bare Wood.

The surface should be clean and dry, sandpapered and dusted off. Apply a first coat of TOPKAPI OPACA onto bare wood, highly diluted up to 50-70% (depending on wood absorption) in order to allow the varnish to sink into the wood substrate. As a clear primer alternative, one coat of POLIGLASS two-component varnish diluted 50-100% (depending on wood absorption) with Thinner 203 can be applied; care should be taken in order to maintain the grain of the wood open so to enable the application of subsequent coats of TOPKAPI OPACA. Overcoat then with 2-3 coats of TOPKAPI OPACA, allowing the required waiting time between coats.

Previously Varnished Wood.

- If the old paint is in poor conditions, loose or powdery, it should be mechanically removed. Clean the surface well and follow application directions as per bare wood.

- If the old paint is in good condition of adhesion and it only needs a topcoat because it is dull or dirty but with the underneath coatings still well fixed to the substrate (with no cracks or bubbles), clean, degrease and sandpaper with medium-fine abrasive paper and apply 2-3 coats of TOPKAPI OPACA, allowing the required waiting time between coats.

Note: In the summer season or when temperatures are higher than 20°C, it is recommended for brush application the use

Codice: 6BA000

Topkapi Opaca

of FLOWING THINNER 109.

Colors



Colore: TRASPARENTE

Cod. Colore: 6BA000

Listino

Formati Disponibili	Codice	Descrizione	Confezione
0.75L	6BA00000750	Topkapi Opaca	0.75 lt

SAFETY PRECAUTIONS

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at laboratorio@aemmecolori.it

NOTES

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of application.